

FIX-IN Silicone bonding

For Mirox,
Lacobel (T) & Matelac (T)

AGC

5
YEAR
WARRANTY



Your Dreams, Our Challenge



IMPORTANT

All FIX-IN products must be stored and handled in compliance with the latest version of the AGC Installation Guide for interior glass applications as well as product technical data sheets, all available on www.agc-store.com or from your local AGC contact. Any local requirements and regulations must be followed. Please contact your local AGC representative in case of questions or translation needs.

FIX-IN Silicone bonding

Prepare the work	– 02
New construction	– 04
Prepare the substrate	– 04
Safety FILM preparation	– 05
Bonding the glass	– 05
Refurbishment	– 08
Prepare the substrate	– 08
Safety FILM preparation	– 09
Bonding the glass	– 09
Tips & tricks	– 12
Warranty	– 12
Disclaimer	– 13



PREPARE THE WORK


0

Pre-requirements before gluing:

- The temperatures of the surfaces to be assembled and of the ambient air must be above 10°C and below 35°C.
- For any given temperature, the relative humidity level must be 5% below the dewpoint level on the surfaces to be glued.
- The surfaces to be glued must be free of all traces of moisture.
- The area around the glazing must be free of dust.

1

Ensure that the silicone is not perished and that it has been stored in a cool and dry place.



2

Make sure to always use FIX-IN SA surface activator when glass has SAFE+ safety film on the back.



3

Observe the specific application procedure for the Lacobel (T) and Matelac (T) colours shown below.

LACOBEL



White Soft
(S-W)
9010



White Pure
(S-W)
9003



White Pearl
(S-W)
1013



Red Luminous
(S-W)
1586



Grey Metal
(S-F)
9006



Taupe Metal
(S-F)
0627



Aluminium
Rich (S-F)
9007



Copper Metal
(S-F)
9115



Black Starlight
(S-F)
0337



Brown Starlight
(S-F)
9015

MATELAC



White Soft
(S-W)
9010



White Pure
(S-W)
9003



White Pearl
(S-W)
1013



Grey Metal
(S-F)
9006



Taupe Metal
(S-F)
0627

LACOBEL T and MATELAC T



Crisp White
(M)
1000

(S-F) = Need safety film when applied with FIX-IN SL.

(S-W) = To be applied on uniform white painted background only.

(M) = Mechanical fixing only (see Installation Guide for more details).

Learn more about AGC's extensive range of Lacobel (T) and Matelac (T) on www.agc-yourglass.com.

NEW CONSTRUCTION

PREPARE THE SUBSTRATE

1

Check and ensure wall flatness and evenness. Clean dust from wall with a brush.



2

Apply FIX-IN PR wall primer on porous surfaces and let it dry. Some Lacobel and Matelac colours require a uniform painted background (see p. 3). No wall primer needed in case of white painted background.



3


Paint a narrow line (max 1 cm) on the joint areas in colours matching the glass and let it dry.



SAFETY FILM PREPARATION

4

- If SAFE+ safety film is present on the back of glass: Apply FIX-IN SA surface activator always in the same direction (from left to right or from right to left, without rubbing it) and clean the back with a dry cloth.



- If no safety film is present, no surface activator is needed. Start bonding the glass.

BONDING THE GLASS

5


Apply FIX-IN AT double sided tape outside the coloured joint area and press firmly to wall.



6

Apply FIX-IN SL silicone in vertical⁽¹⁾ lines or dots on the wall, observing recommended distances (see table below), depending on glass thickness.

FIX-IN SL



			 1m ⁽¹⁾
	FIX-IN AT	4 mm 6 mm 8-10 mm	2 3 4
	FIX-IN SL	4 mm 6 mm 8 mm 10 mm	4 5 6 7

⁽¹⁾ Minimum running m per m²

7

Apply additional silicone close to cut-outs and holes.




8

Remove protection film from FIX-IN AT and use setting blocks to support glass.




9

Start installation at outer edge. Position and adjust the sheet whilst floating on silicone.



10

Once well positioned, press firmly on glass for adhesion to tape.




11

Use metal profiles for outer corners to improve the resistance.



12

Allow at least 48h drying time before removing setting blocks.



13

In moist areas, always seal joints. Whilst sealing joints, protect glass with masking tape and remove tape as soon as silicone is applied.



REFURBISHMENT

PREPARE THE SUBSTRATE

1

Check tiles for hollow areas, remove loose parts.



2

Check and ensure wall flatness and evenness.




3

Clean tiles with water + a drop of ammonia (NH_4OH).



4

Paint the wall on the joint areas in colours matching the glass and let it dry. Some Lacobel and Matelac colours require a uniform white painted background (see p. 3).



SAFETY FILM PREPARATION

5

- If SAFE+ safety film is present on the back of glass: Apply FIX-IN SA surface activator always in the same direction (from left to right or from right to left, without rubbing it) and clean the back with a dry cloth.



- If no safety film is present, no surface activator is needed. Start bonding the glass.

BONDING THE GLASS

6

Apply FIX-IN AT double sided tape outside the coloured joint area and press firmly to the tiles or the glass wall.



7

Apply FIX-IN SL silicone in vertical⁽¹⁾ lines or dots on tiles or glass matching recommended distances (see table below), depending on glass thickness.

FIX-IN SL




			 1m ⁽¹⁾
	FIX-IN AT	4 mm 6 mm 8-10 mm	2 3 4
	FIX-IN SL	4 mm 6 mm 8 mm 10 mm	4 5 6 7

⁽¹⁾ Minimum running m per m²


8

Remove protection film from FIX-IN AT and use setting blocks to support glass.



9

Start installation at outer edge. Position and adjust the sheet whilst floating on silicone.



10

Once well positioned, press firmly on glass for adhesion to tape.



11

Use metal profiles for outer corners to improve the resistance.



12

Allow at least 48h drying time before removing setting blocks.



13

In moist areas, always seal joints. Whilst sealing joints, protect glass with masking tape and remove tape as soon as silicone is applied.



TIPS & TRICKS

1. To easily rectify the placement of large sheets of glass during installation:
 - a) apply FIX-IN AT 10 cm above the lower edge of the sheet
 - b) apply FIX-IN SL in vertical lines or in dots larger than the FIX-IN AT (3.21 mm).
2. Silicone FIX-IN SL can also be used for sealing joints.
3. If there are traces of silicone on the glass side, products for cleaning silicone on glass (including matt glass) can be purchased on the site www.agc-store.com. These products can be used to remove dry silicone as well as fresh silicone. A video of this easy and effective cleaning process can be viewed on the home page of the site.

All FIX-IN products may be purchased online on the www.agc-store.com. Be sure to view the tutorials on the home page.

WARRANTY

AGC offers a 5-year warranty on Lacobel, Matelac and Mirox products and a 10-year warranty on Lacobel T and Matelac T products against discoloration, cracking and peeling of the paint*. This warranty applies only if FIX-IN products have been used in full compliance with the latest version of this Installation Guide, which can be either consulted on www.agc-store.com or obtained from your local AGC representative. AGC is not responsible for products or materials produced or supplied by third parties.

*See warranty conditions available on www.agc-store.com or from your local AGC representative.

DISCLAIMER

1. This document (the "Document") is the full and exclusive ownership of AGC Glass Europe SA, with registered office at Avenue Jean Monnet 4, 1348 Louvain-la-Neuve, Belgium, and registered with the Crossroads Bank for Enterprises under No. 0413.638.187 ("AGC Glass Europe"), and is part of the technical documentation of AGC Glass Europe. All intellectual property rights in the content of the Document as well as any products mentioned therein are held by or licensed to AGC Glass Europe. The customer ("Customer") can only use the Document for the sole purpose of installing AGC glass products. The Document confers no other right, title or interest to the Customer.
2. The above right to use the Document is granted by AGC Glass Europe free of charge. The Customer should on a regular basis check for any updates of the Document on www.agc-store.com or by consulting their local AGC contact.
3. AGC Glass Europe has made every effort to ensure the accuracy of the information in this Document, but it can not be held liable for any typographical or other errors, inaccuracies, omissions and oversights in the Document.
4. The Customer is responsible for ensuring that their plans are compliant with all relevant requirements, standards and regulations. To the maximum extent permitted under applicable law, AGC Glass Europe is not liable for any damages or losses whatsoever that could result, whether directly and/or indirectly, from the use of the Document by the Customer, and the Customer shall always hold AGC Glass Europe harmless from and against, and indemnify AGC Glass Europe in full for any actions, claims, demands, proceedings, suits, and any other recourses whatsoever, whether in court or otherwise, initiated by third parties in relation to the Document and its use.
5. The Customer shall contact in due time an AGC expert in order to jointly determine the appropriate composition and specifications of the glass products to be used in the project.
6. Compliance with the recommendations set out in this Document does not exempt the Customer from complying with any and all specific local requirements in the Customer's own country as well.
7. By using the Document, the Customer irrevocably acknowledges and agrees having read, understood and agreed to all the terms and conditions mentioned in the Document.

Dealer's stamp



9001145 - CC - 01/2020

AGC GLASS EUROPE

UNITED KINGDOM - AGC Glass UK -

T +44 1788 53 53 53 - sales.uk@eu.agc.com

OTHER COUNTRIES - AGC Glass Europe -

T +32 2 409 30 00 - sales.headquarters@eu.agc.com

AGC Glass Europe has representatives worldwide.

See www.agc-yourglass.com for further addresses.

